

TECHNICAL DATA SHEET

EarthBi IM 502 (M)

DESCRIPTION

EarthBi is a bio-based polymer produced from renewable sources and belonging to the PLA family. Like other bio-based polymers, EarthBi offers a significant reduction in the carbon footprint compared to fossil-based plastics.

EarthBi IM 502 (M) is a grade under development that can be used in injection moulding processes. It has been formulated to be compatible with other thermoplastic polymers with a low transformation temperature to produce compostable and biodegradable objects and manufactured.

PROCESSING INFORMATION

EarthBi IM 502 (M) is available in pellets. The polymer is amorphous and therefore is susceptible to forming blocks at temperatures above the glass transition temperature (T_g). The polymer in the molten state is stable provided that the guidelines for extrusion and drying are correctly applied. EarthBi polymers are processed in conventional extruders for compounds. Excessive friction during compounding degrades the polymer so a temperature between 170 and 190 ° C is recommended. Since EarthBi IM 502 (M) is amorphous and with a low T_g, the use of a twin-screw extruder is recommended as the use of a single-screw extruder could cause the pellets entering the screw to stick.

PHYSICAL PROPERTIES IM 502 (M)

| PHYSICAL PROPERTIES | METHOD | TYPICAL VALUE |
|---------------------------|-----------------|---------------|
| Form | | Round Pellets |
| Yellowness Index | ASTM D6290 | 60 |
| Density (g/ml) | ISO 1183 | 1,24±10% |
| Glass Transition (°C) | DSC | 46±2 |
| Residual Monomer (%w/w) | Gas Chrom. | <0,3 |
| Moisture (ppm) | Karl-Fisher | <250 |
| MFI 2,16 Kg/190°C (g/10') | ISO 1133-1 | 30±5 |
| Relative Viscosity | Internal method | 2,2±0,2 |

MOISTURE & PRE-DRYING

It is recommended to keep the polymer in its original sealed packaging until it is used and fed to the degassed twin-screw extruder. Residual moisture can be removed in the first degassing area at moderate vacuum values (50 mmHg). The polymer must always be stored in a cool and dry place at a temperature below 40 °C.

PACKAGING & STORE CONDITIONS

EarthBi IM 502 (M) is available in octabins with 750 kg aluminized internal liner bags and on request in 20 kg boxes. PLA polymers are recommended to be stored in their original closed moisture barrier packaging at temperatures below 40 °C. Storage in direct sunlight should be avoided.

